

P.O. Box 644 (42702)
209 Peterson Drive
Elizabethtown, KY 42701

Phone: 270-737-6757
Toll Free: 800-626-4403
Fax: 270-737-6241

Website: www.inland-inc.com
Email: inland@inland-inc.com

INNERBOND C-770 STONE, MARBLE & GRANITE CAULK 100% RTV SILICONE

INNERBOND C-770 Stone, Marble & Granite Caulk is a 100% silicone adhesive sealant specially formulated to adhere to non-porous surfaces such as cultured marble, granite and natural stone. C-770 provides a flexible, mildew resistant, watertight seal for both interior and exterior use.

Innerbond C-770 Stone, Marble & Granite Caulk offers the following features:

- Interior and exterior use
- Permanently flexible, watertight seal
- Cured sealant is mildew resistant

USES

Innerbond C-770 Stone, Marble & Granite Caulk is an exceptionally versatile silicone rubber. Typical applications include:

- Caulking baths, showers, and sinks.
- Bonding and sealing appliance parts, nameplates/signs and screwless brackets.
- Apply to joints around backsplashes, sinks, countertops, bathtubs, basins, toilets, showers & ceramic tile.
- Adheres to glass, wood, metal, porcelain, ceramic tile and painted surfaces

TYPICAL PROPERTIES

COLORS	Various	SPECIFIC GRAVITY AT 77°F (25°C)	1.03
EXTRUSION RATE (3.18mm orifice, 90 psig)	400 g/min	FLOW RATE (sag/slump on 3.18 x 101.6 mm bead)	Nil
TACK-FREE TIME AT 77°F (25°C) and 50% RH	10-20 minutes	DUROMETER HARDNESS, SHORE A, POINTS	27
CURE TIME AT 77°F (25°C) and 50% RH (3.18mm thickness)	24 hours	TENSILE STRENGTH, psi (MPa)	350(2.4)
ELONGATION	600%	BRITTLE POINT	-80°F (-62°C)
HIGH SERVICE TEMPERATURE LIMIT	+450°F (+232°C)	DYNAMIC MOVEMENT CAPABILITY, PERCENT	±25%

LIMITATIONS

Innerbond C-770 Stone, Marble & Granite Caulk will corrode and/or not adhere to copper, brass (and other copper-containing alloys), magnesium, zinc and galvanized metals (and other zinc-containing alloys). This sealant is not recommended for use on brick masonry and cementitious substrates, or surfaces which will be painted. (The paint film will not stretch with the extension of the sealant and may crack or peel. Paint first, then apply sealant thereafter.) Best adhesion and compatibility are not achieved with substrates made of methylmethacrylate (PLEXIGLAS), polycarbonate, polypropylene, polyethylene and polytetrafluoroethylene (TEFLON®). This sealant is not recommended for below-grade applications, total water immersion situations or for joints with extreme movement. It is further not intended for structural glazing. Do not use in areas where abrasion and physical abuse are encountered.

HOW TO USE

Innerbond C-770 Stone, Marble & Granite Caulk adheres to many clean surfaces without the use of primers. These surfaces include glass, ceramic, many metals, some rigid plastics and silicone rubber. Innerbond C-770 will also produce a fair bond to some flexible plastics (which do not contain plasticizers) and to organic rubber. For any applications, an evaluation should be made to determine bond strength.

To prepare surfaces for maximum adhesion, first clean with suitable solvents such as MEK (methyl ethyl ketone), naphtha, or 1,1,1-trichloroethane to remove all grease, dirt and oil. All solvents must be wiped from surfaces before the sealant is applied. For best results apply at a temperature no lower than 50°F. The sealant should be tooled immediately after application and before a skin forms, using light pressure to spread it against the substrate. Uncured sealant may be cleaned from non-porous surfaces and tools using a solvent such as xylene. On porous surfaces, allow the sealant to cure and remove by abrasion.

Cure time is affected by relative humidity, degree of confinement and cross-sectional thickness of the sealant. Sections up to 1/8-inch thick become rubbery solids in about 24 hours at room temperature at 20 percent relative humidity. More moisture content reduces cure time slightly. Curing time increases with the thickness of the sealant. A 1/2-inch cross-section, for example, may require 3 or 4 days for complete solidification. However, the cure will have penetrated the outer 1/8-inch in about 24 hours.

In applications where Innerbond C-770 Stone, Marble & Granite Caulk may be partially or totally confined during cure, the time required for proper cure is generally lengthened by the degree of confinement. It is possible that with absolute confinement cure will not be completed. The result is the softening of the sealant at elevated temperatures. Metal-to-metal bonds should not overlap more than one inch. Every application involving confinement during cure should be thoroughly tested before field application.

CAUTION

Uncured Innerbond C-770 Stone, Marble & Granite Caulk will irritate the eyes. In case of contact with eyes, flush with water for 15 minutes and consult a physician. The uncured sealant may also irritate the skin. Prompt removal by wiping with a dry cloth or paper towel, followed by washing the skin with soap and water is recommended.

Innerbond C-770 Stone, Marble & Granite Caulk releases acetic acid vapors during the curing period. Effective ventilation must be maintained during application and curing to limit the concentration of acetic acid vapor (which is irritating to the eyes and breathing passages). Wearing of contact lenses during use should be avoided because vapor may be trapped behind the lenses. Use only in well-ventilated work areas.

Product Material Safety Data Sheets are available upon request.

PACKAGING

Innerbond C-770 Stone, Marble & Granite Caulk is provided in 10.1 ounce cartridges, packed 12/case.

NOTE

The information and data contained herein are believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since Inland, Inc. cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose.

Thorough testing of our product on any proposed use should be conducted prior to each application. It is the responsibility of the consumer to evaluate the performance of our product in each given application. Likewise, if the manner in which our products are used requires governmental approval or clearance, it is the user's responsibility to obtain it.

Inland, Inc. warrants only that each product will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other expressed or implied warranties. The user's exclusive remedy and Inland, Inc.'s sole liability is limited to replacement of any product shown to be otherwise than as warranted. Inland, Inc. will not be liable for incidental or consequential damages of any kind.

Suggestions of uses should not be taken as inducements to infringe any patents.